

UPM Finesse Silk



PRODUCT INFORMATION

UPM Finesse Silk is a high quality, wood-free coated digital printing paper with a smooth silky finish. The ideal choice of substrate when producing impressive, eye catching and prestigious printed media.

STOCK SCHEDULE

RW = REAM WRAPPED / BP = BULK PACKED

| MM | gsm | 90 | 100 | 115 | 130 | 150 | 170 | 200 | 220 | 250 | 270 | 300 | 350 | 400 |
|----------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|
| 320x450 | | | | BP/RW | BP/RW | BP/RW | BP/RW | | | | | | | RW |
| 450x320 | | | | | | | | RW | | RW | | RW | RW | RW |
| 460x320 | | | | | | | | | | | | | | RW |
| 480x650 | | | | BP/RW | BP/RW | BP/RW | BP/RW | RW | | RW | | RW | RW | |
| 450x640 | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW |
| 520x720 | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | RW | BP/RW | RW | BP/RW | BP/RW | BP/RW |
| 530x750 | | | | | | | | RW | | RW | | RW | RW | RW |
| 750x530 | | | | BP/RW | BP/RW | BP/RW | BP/RW | | | | | | | |
| 630x880 | | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | | | | | | |
| 880x630 | | | | BP/RW | BP/RW | BP/RW | BP/RW | | | | | | | |
| 640x900 | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW |
| 900x640 | | | | BP/RW | BP/RW | BP/RW | BP/RW | | | | | | | |
| 720x1020 | | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | RW | BP/RW | RW | BP/RW | BP/RW | BP/RW |
| 1020x720 | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | BP/RW | | | | | | | |

SPECIFICATION

| Technical Information | | | | | | | | | | | | | |
|-------------------------------------|------|------|-----|-----|------|-----|-----|-----|------|------|------|------|------|
| Grammage | 90 | 100 | 115 | 130 | 150 | 170 | 200 | 220 | 250 | 270 | 300 | 350 | 400 |
| Thickness (mic) | 76 | 83 | 97 | 110 | 131 | 157 | 185 | 232 | 232 | 275 | 290 | 350 | 404 |
| Brightness D65 | 100 | 100 | 100 | 100 | 100 | 100 | 100 | 100 | 100 | 100 | 100 | 100 | 100 |
| CIE Whiteness | 127 | 127 | 127 | 127 | 127 | 127 | 127 | 127 | 127 | 127 | 127 | 127 | 127 |
| Opacity | 91.5 | 92.5 | 95 | 96 | 97.5 | 98 | 99 | 99 | 99.5 | 99.6 | 99.8 | 99.9 | 99.9 |
| Gloss Hunter (ISO 8254-1) (%) | 24 | 24 | 24 | 24 | 24 | 24 | 24 | 24 | 24 | 24 | 24 | 24 | 24 |
| Smoothness PPS 10 (ISO 8791-4) (µm) | 2 | 2 | 2 | 2 | 2 | 2 | 2 | 2.2 | 2 | 2.2 | 2 | 2 | 2.5 |

ENVIRONMENTAL STANDARDS



BfR Food Certificate, 94/62 EC Heavy Metal Certificate

The above information is given for general guidance only and is subject to change without notice.

