
# White Peak GC1

### Fully coated hard sized folding boxboard with single coated white back GC1 (FSC<sup>®</sup> certified).

#### **BOARD PROFILE**



Double blade coating Bleached chemical pulp (ECF) Bleached Thermo Mechanical Pulp and mill broke Bleached chemical pulp (ECF) Single coating

#### **PRODUCT INFORMATION**

- ISO 9000:2000 and ISO 14001 approved supplier.
- All pulp is sourced from well managed and sustainable forests and is fully recyclable. (FSC® Mix Credit).
- The bleached pulp is ECF.
- Certified for safety with direct contact with dry and non fatty foods (ISEGA). Suitable for frozen food cartons. (Hard-sized).
- Conforms to European standards regarding heavy metal content.
- Cobb Value Top and Back (1min) 25-45 gsm

#### **PROCESS SUITABILITY**

- Litho
- Gravure
- Screen printing
- Letterpress
- Flexo
- UV and litho varnishing
- Emulsion coating
- Foil and film laminating
- Embossina
- Foil blocking

#### **TYPICAL USES**

- GRAPHIC Book covers, folders, greeting cards, post cards, point of sale displays, CD and video sleeves.
- PACKAGING Cartons for cosmetics, health care and pharmaceuticals, frozen, chilled and other foods, drinks, toys and games.

#### SPECIFICATION Sheet stock weights indicated\*

	Microns	g/m2	Stiffness - Taber 15° mN.m	
			MD	CD
	300	205	5.8	2.8
	345	225	8.2	4.0
	370	240	11.7	5.7
	405*	255*	14.9	7.2
	455*	280*	19.8	9.6
	500*	300*	24.3	11.3
	550*	330*	31.4	14.2
	600*	360*	39.0	17.2
	660	390	47.0	20.5
Tolerance	+/-5%	+/-5%	-10%	-10%
	Gloss		(Hunter 75°) >40 (PPS) <1.0µm +/- 0.5 (TAPPI) 87% -2 +1(top) 84% -2 +1 (back)	
	Smoothness			
	Brightness			
	Cobb Value Top and Back (1min) 25-45 gsm			

Indent mill makings are available in all the thicknesses listed above.

The above information is given for general guidance only and is subject to change without notice.



## www.paper.co.uk



