

Oppboga Excellent™

Virgin fibre board, triple coated on both sides

SUB-STANCE	THICKNESS		BENDING RESISTANCE L&W 15° mN		BENDING MOMENT Taber 15° mNm	
	g/m ²	mic	pt	MD	CD	MD
370	505	20	550	265	27	13
400	620	24	900	475	44	23
450	680	27	1125	575	55	28
500	800	31	1725	825	84	40
620	1000	39	2575	1485	125	72
770	1250	49	2250 ¹	1075 ¹	*	*
880	1500	59	3375 ¹	1600 ¹	*	*
1000	1750	69	*	*	*	*
1100	2000	79	*	*	*	*
1400	2500	98	*	*	*	*
1600	3000	118	*	*	*	*
1850	3500	138	*	*	*	*
2140	4000	158	*	*	*	*

¹L&W 5° mN

Highlighted products are available from stock

*values cannot be measured



The natural choice for indoor advertising.

APPLICATIONS

Indoor Sign & Display

PRINTING

Offset printing • screen printing • large format digital printing

CONVERSION

Embossing • foil and film lamination • varnishing • die cutting • creasing • perforating • cutting and scoring

ADDITIONAL INFORMATION

www.oppboga.com

Tolerances / Testing Standards

Grammage (DIN ISO 536)	±10%
Thickness (DIN ISO 534)	±10%
Bending stiffness (ISO 5629)	-15%
Brightness C/2° (ISO 2470)	min. 87
Surface smoothness (ISO 8791-4)	max. 1.7

Printing Surface Properties

ISO Brightness	90
CIE Whiteness D65/10° (ISO 11475).....	120
Surface smoothness (PPS).....	1.0 m
Gloss 75° (ISO 8254-1).....	45%



The mark of responsible forestry
FSC® C016680