



kraftpak[®]
Simply Natural

PRODUCT INFORMATION

KraftPak is a single-ply uncoated unbleached kraft paperboard that offers a consistent and uniform surface with an attractive natural brown appearance. The unique look and feel truly delivers the ideal combination of sustainability and durability to help stand out.

KraftPak is a versatile, sustainable fit in a wide variety of applications.

SUGGESTED USES ● Automotive ● Clothing tags ● Filter frames
● Wedding stationery ● Beverage carriers ● Wines and spirits
● Dry and prepared food ● Food service/carry-out ● Gift boxes
● Health and beauty ● Slip sheets/partitions ● Sporting goods



PROCESS SUITABILITY

Suitable for die cutting, embossing, foil laminating, flexo, letterpress, paper laminating, screen printing and litho printing.

STOCK SCHEDULE

micron	381	432	457	508	559	610	660
gsm	258	288	302	332	356	380	410
720 x 1020 mm	●		●	●		●	●

● Available from stock for next day delivery subject to availability
All other weights available from mill makings, please enquire for details.

SPECIFICATION

Technical Information								
Grammage (gsm)		258	288	302	332	356	380	410
Thickness (mic)		381	432	457	508	559	610	660
Moisture Content (%)		5.8	5.8	5.8	5.8	5.8	5.8	5.8
Stiffness (Taber 15°) (mNm)	MD	11.8	16.2	19.6	26.5	30.9	38.2	45.1
	CD	5.4	6.4	8.3	10.8	14.2	17.2	21.1
	GM	8.0	10.2	12.8	16.9	21.0	25.6	30.8

Respectivity								
Grammage (gsm)		258	288	302	332	356	380	410
Cobb (2min.)	Top	40	40	40	40	40	40	40
	Bottom	40	40	40	40	40	40	40
ZDT (kPa)		450	380	380	380	340	340	310
Coefficient of Friction (CoF)		0.35	0.35	0.35	0.35	0.35	0.35	0.35

Smoothness & Permeability								
Grammage (gsm)		258	288	302	332	356	380	410
Sheffield (SU)	Top	380	390	400	405	390	395	400
	Bottom	370	380	390	395	380	385	390
Gurely Porosity (sec/100ml)		15	15	15	15	10	10	10
Tear (N)	MD	4.9	5.7	5.9	6.1	6.9	7.3	8.2

Values are subject to change without notice.

ENVIRONMENTAL CREDENTIALS



The CO₂ emissions from this product can be mitigated through the Carbon Capture[®] programme, directly supporting the work of the Woodland Trust.

The above information is given for general guidance only and is subject to change without notice.